

AMENDMENTS TO CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the present application.

We Claim:

1. (Currently Amended) A molding composition ~~containing~~ comprising:
polyamide[,];
0.1 to 8 parts by weight of electrically conductive carbon in particulate form
selected from the group consisting of carbon black, graphite and carbon nanofibrils;
and
0.5 to 50 parts by weight of a graft polymer, wherein said graft polymer is the product of polymerizing at least one monomer selected from the group consisting of styrene, a-methylstyrene, halogen-substituted or alkyl-ring-substituted styrenes, (meth)acrylic C₁-C₈ alkyl esters, methyl methacrylate, n-butyl acrylate and tert-butyl or mixtures thereof and at least one monomer selected from the group consisting of unsaturated nitriles, acrylonitrile, methacrylonitrile, (meth)acrylic C₁-C₈ alkyl ester, methyl methacrylate, n-butyl acrylate, tert-butyl acrylate, derivatives of unsaturated carboxylic acids, maleic anhydride and N-phenylmaleimide or mixtures thereof, grafted on a graft base having glass transition temperature < 10° C, with the proviso that EPR or EPDM rubber based graft polymers are excepted,
wherein the sum of the parts by weight of the polyamide, conductive carbon and graft polymer totalling 100, and
wherein said molding composition does not consist of polyphenylene ether or modified polyphenylene ether.
2. (Currently Amended) ~~A-The molding composition of Claim 1, further containing comprising polyamide, 0.1 to 8 parts by weight of electrically conductive carbon in particulate form, 0.5 to 50 parts by weight of a graft polymer, and up to 30 parts by~~

PO-7826

- 2 -

weight non-carbon based mineral particles the sum of the parts by weight of the polyamide, conductive carbon, graft polymer and non-carbon based mineral particles totalling 100.

3. (Cancelled)

4. (Currently Amended) ~~A thermoplastic~~ The molding composition of Claim 1, comprising

A) 40 to 90 parts by weight polyamide

B) 0.5 to 50 parts by weight of said graft polymer

C) 0.1 to 30 parts by weight non-carbon based mineral particles

D) 0.1 to 8 parts by weight electrically conductive carbon particles

the sum of the parts by weight of A) through D) totalling 100, said molding composition being thermoplastic.

5. (Cancelled)

6. (Cancelled)

7. (Currently Amended) The composition according to Claim 51, wherein ~~the~~ said graft base is at least one member selected from the group consisting of diene rubbers, copolymers of diene rubbers, acrylate rubbers, polyurethane/silicone rubbers, chloroprene rubbers and ethylene/vinyl-acetate rubbers.

8. (Currently Amended) The composition according to Claim 51, wherein ~~the~~ said graft base is at least one member selected from the group consisting of diene rubbers, copolymers of diene rubbers and acrylate rubbers.

PO-7826

- 3 -

9. (Currently Amended) The composition according to Claim ~~5~~1, wherein the graft base is polybutadiene.
10. (Cancelled)
11. (Currently Amended) The composition according to Claim 2, wherein the non-carbon based mineral particles are selected from the group consisting of talc, mica, clay-bank minerals, montmorillonite, kaolin, vermiculite and wollastonite.
12. (Currently Amended) The composition according to Claim 2, wherein non-carbon based mineral particles are talc.
- 13.-14. (Cancelled)
15. (Original) A molded article comprising the composition of Claim 1.
16. (Original) A molded article comprising the composition of Claim 4.

PO-7826

- 4 -